



**ABS**

**SD0150**

**Typical data - SD0150**

PROPERTY	TEST METHOD	UNIT	VALUE
MELT FLOW INDEX(200 C/5KG)	ASTM D-1238	GR/10MIN	1.8
IZOD IMPACT STRENGTH	ASTM D-256	KJ/M2	22
VICAT SOFTENING POINT(50 N LOAD)	ASTM D-1525	°C	98
BULK DENSITY	-	KG/M3	600
TENSILE STRENGTH AT YEILD	ASTM D-638	KGF/CM2	450
ROCKWELL HARDNESS(AT 23 C)	ASTM D-785	R.SCALE	105

**Producer: Tabriz Petrochemical Company (T.P.C)**



**MIRA PETROKEM** Dis Tic. Ltd. Sti.

Merkez Mah. Akar Caddesi No:3 İTower Plaza Kat:7 No:43 Şişli/İstanbul

Tel: +90 212 2203422

Email : [Info@mirapetrokem.com](mailto:Info@mirapetrokem.com)