



HDPE FILM

7000 F (FILM GRADE)

High Density Polyethylene

Property	Test Method	Value	Unit
Resin Properties			
Melt Flow Rate	ASTM D 1238 @ 190 ° C, 2.16 kg	0.04	g/10 min
Density	ASTM D 1505	0.954	g/cm ³
Melting Point	ASTM D 2117	131	° C
Vicat Softening Point	ASTM D 1525	124	° C
Brittleness Temperature	ASTM D 746	< -60	° C
ESCR	ASTM D 1693 @ 50 ° C	> 1000	hrs, F50
Film Properties			
Tensile Strength at Yield	ASTM D 638 @ crosshead speed 50mm/min	MD: -*, TD: 250*	kg/cm ²
Tensile Strength at Break	ASTM D 638 @ crosshead speed 50mm/min	MD: 620*, TD: 310	kg/cm ²
Tensile Modulus, 2% Secant	ASTM D 638 @ crosshead speed 50mm/min	MD: 8200*, TD: 8000*	kg/cm ²
Elongation at Break	ASTM D 638 @ crosshead speed 50mm/min	MD : 240*, TD : 450*	%
Elmendorf Tear Strength	ASTM D 1922	MD : 3*, TD : 80*	g
Dart Impact Strength	ASTM D 1709	139*	g

Producer: Mehr Petrochemical Company (MHPC)



MIRA PETROKEM Dis Tic. Ltd. Sti.

Merkez Mah. Akar Caddesi No:3 İTower Plaza Kat:7 No:43 Şişli/İstanbul

Tel: +90 212 2203422

Email : Info@mirapetrokem.com